

DESCRIPTION

PU 110 is a single component, easily applied, polyurethane based, liquid waterproofing membranes. It creates an elastic and durable film layer by curing with the humidity in the air.

TYPICAL APPLICATIONS

- Car parks,
- Irrigation channels,
- Asphalt membranes,
- Gypsum and cement panels,
- Exposed roofs,
- Indoor and outdoor applications,
- Terrace, veranda and balconies,
- Wet areas in indoor (bathroom, kitchen and etc.).

FEATURES AND ADVANTAGES

- PU 110 is Certified according to ETAG 005, W3 category.
- Easy to apply (by brush, roller or spray).
- When applied it forms a one-piece layer that does not cause joint formation or leakage.
- Resistant to continuous water contact.
- Preserves its mechanical properties between -40°C and +90°C.
- It is permeable to water vapor. Having a breathable structure it does not cause accumulation in the substrate.
- When the material is damaged, it can be repaired easily and quickly with PU110.
- Excellent UV resistance.
- Excellent chemical resistance.

CONCRETE SUBSTRATE STANDARDS

- Hardness: R28 = 15 Mpa
 - Humidity: W <10%
 - Temperature: + 5 °C and + 35 °C
 - Relative Humidity: <85%
- For detailed information, please consult our technical department.

APPLICATION PROCEDURE

• SURFACE PREPERATION

In order to ensure a good adhesion oil, grease, paraffin waste, cement grout, loose particles, mold release agents, cured old membranes should be removed from the surface before the application. The surface should be thoroughly dried after washing with high pressure water and should be free from damp. Surface defects and cracks should be repaired with suitable products.

• PRIMING

For absorbent surfaces such as concrete, cement or screed, PU PRIMER 200 or EPOXY PRIMER should be used. AQUA PU PRIMER 2K or EPOXY PRIMER WB should be preferred on damp surfaces. TILE PRIMER should be used on non-absorbent surfaces such as metal, ceramic or old coatings. Please examine primer table for detailed information.

• APPLICATION

Before using, the package should be opened and mixed with a low speed mixer for 2-3 minutes. For spray application, add CLEVER 001 at a maximum rate of 5% - 7%. The primed surface should be applied with a roller, squeegee or brush until the entire surface is covered, by pouring the product within minimum 2 layers. After the first layer is applied, the second layer should be applied minimum 6 hours and maximum 24 hours later. If the application has not been made within the specified time for the second layer, please consult the technical office of CLEVER POLYMERS for information and solutions before application. In order to increase the acceleration of the drying in cold weather, it is recommended to use ACC CATALYST if desired. Consult our technical department for thinning process.

THE APPLICATION METHOD FOR W3 DURABILITY ACCORDING TO ETA-23/0032

1 Primer: Clever Epoxy Primer
 2 Waterproofing: CLEVER PU 110 as two layers
 3 Interlayer : White and 110 gr/m² felt
 After the surface is cleared from separator layers and mechanically wiped, EPOXY PRIMER is applied on it as 0.5-0.60 kg/m². Before the epoxy primer gets dry, 0.3-0.7 mm silica sand is sprinkled on it. After 24 hours, the silica sand on the surface is cleared and PU 110 application starts. Before use, the package should be opened and mixed with a low speed mixer for 2-3 minutes. PU 110 is applied to the surface with a roller or squeegee as one coat and a 110 gr/m² white polyester felt is laid on the product before it gets dry, and a second coat of PU 110 should be applied on it again. In this system, the amount of PU 110 that should be used is min 2.0 kg/m². Total system thickness should be 2.3 mm

APPLICATION REMARKS

- It should be covered with PU 650 TC-1K or PU 600 TC-1K aliphatic flexible top coat material in order to extend the strength and shelf life of polyurethane based waterproofing products which are applied to areas exposed to open air conditions or pedestrian traffic.
- Not recommended for loose and unstable surfaces.
- It is not used for waterproofing of swimming pools with chemically treated water.

CONSUMPTION

- First Layer (minimum): 0,70 - 0,90 kg/m²
- Second Layer (minimum): 0,70 - 0,90 kg/m²
- Airless Spray (for each layer): 0,75 - 0,90 kg/m²
- Total Consumption (minimum): 1,40 - 1,80 kg/m²

CLEANING

After the application, all tools should be cleaned with CLEVER 001. Rollers and brushes should be disposed of.

PACKAGING AND COLOR

It is white and grey in 5 kg and 25 kg metal buckets.

STORAGE AND SHELF LIFE

The product can be stored for a maximum of 12 months in unopened original pail at temperatures between + 5°C and +25°C. Opened product should be used at the soonest.

PRECAUTIONS

The product should be used in well ventilated environments. The product should not be in contact with open fires. Smoking should not be allowed during application. Protective gloves and masks should be used for hands and eyes during application. If the material comes into contact with eyes, it should be washed immediately with sufficient water. For more detailed information, ask for the Safety Data Sheet (MSDS) from CLEVER POLYMERS technical department.



TECHNICAL DATA

QUALIFICATION	METHOD	FEATURE
Coating Type	Clever Lab.	Single Component Polyurethane
Density	ASTM D 1475 / EN ISO 2811-1 (+20°C)	1,40 ±0,05 gr/cm ³
Viscosity	ASTM D4287 (+25°C)	3000 - 6000 cp
Flash Point	ASTM D93	35 °C
Water Vapor Permeability	ASTM E96	0,8 gr/m ² hour
Gloss	Clever Lab.	Semi-Gloss
Application Temperature	Clever Lab.	+5°C to +35°C
Shock Heat Resistance	Clever Lab.	200°C - Passed
Solid Content	Clever Lab.	%85 (±5)
Hardness	ASTM D2240, DIN 53505, EN ISO R868	60 (Shore A)
Elongation at Break	ASTM D 412 (+23°C)	> %500
Tensile Strength	ASTM D 412 (+23°C)	> 6 N/mm ²
Adhesion to Concrete	TSE EN 1542 (+23°C)	> 2 N/mm ²
QUV	ASTM G53	2000 hours - Passed
Service Temperature	Clever Lab.	-40 to +90°C
Tack Free Time	25°C / 55% RH	4 hours
Recoat Time	Clever Lab.	6 to 24 Hours
Hydrolysis (%8 KOH, 15 days at 50 °C)	Clever Lab.	No significant change observed in elastomeric characteristic
Hydrolysis (H ₂ O, 30 days rotative, 60-100 °C)	Clever Lab.	No significant change observed in elastomeric characteristic
HCl (PH=2, 10 day at RT)	Clever Lab.	No significant change observed in elastomeric characteristic
Hydrolysis (H ₂ O, RT 100 °C 14 days rotative)	Clever Lab.	No significant change observed in elastomeric characteristic
Thermal Resistance (100 days at 80 °C)	EOTA TR011	Passed

* Viscosity measured at + 25°C according to EN ISO 3219 standards. Viscosity increases inversely with temperature.

CLASSIFICATION ACCORDING TO EOTA GUIDELINE (EUROPEAN ORGANISATION OF TECHNICAL APPROVAL)

REQUIREMENT	PU 110	PU 110
Minimum Expected Working Life	W3 (25 years)	W2 (10 years)
Climatic Zone	S (severe)	
Used Load	P1	P3
Roof Slope	S1-S4	
Minimum Surface Temperature	TL3 (-20 °C)	
Maximum Surface Temperature	TH4 (90 °C)	TH3 (80 °C)
Exposure To External Fire	Broof (t1,t4)	
Reaction To Fire	Class E	



CLEVER POLİMER VE YAPI KİMYASALLARI A.Ş.

Köseler Mah. 34. Cadde No:5 41455 Dilovası / KOCAELİ / TURKEY

Tel: +90 (262) 728 14 12 Fax +90 (262) 728 14 13

e-mail: info@cleverpolymers.com

www.cleverpolymers.com

NOTE: This document is not a product description statement, all information is given in good intention. This information is out of warranty as the conditions of use are beyond the control of the manufacturer. The final assessment of the suitability of any information, whether implied or not, or the use of the material contemplated, the way of use, and whether there is a breach of patents is the sole responsibility of the user. The manufacturer assumes no liability for coverage / consumption, performance or damage in product use. Consult Clever Polymers for detailed advice / recommendations for applications in special conditions. This technical document is valid until the new one is printed and makes old editions invalid.